

Epilox[®] P 13-18

Description

Epilox[®] P 13-18 is a clear, colourless liquid.

Data

Viscosity at 25 °C (DIN 53 015)	mPa·s	5 - 10
Epoxy Equivalent Weight (DIN 16 945)	g/mol	270 - 305
Density at 20 °C (DIN 53 217 T.4)	g/cm ³	ca 0.89

Use

Epilox[®] P 13-18 is a reactive diluent for epoxy resins.
Epilox[®] P 13-18 is easily miscible with epoxy resins and can therefore be used to reduce the viscosity of standard epoxy resins, e.g. Epilox[®] A 19-00 or Epilox[®] A 19-02.

Packing/Storage/ Transportation

Epilox[®] P 13-18 is supplied in drums, containers or tank trucks.
The product should be stored in closed containers at temperatures between 10 °C and 30 °C to protect it from moisture. Under these storage conditions, Epilox[®] P 13-18 shows no change in quality even after prolonged storage time exceeding 12 month.

Safety Requirements

Epilox[®] P 13-18 is labelled "Xi" and "N" in accordance with the provisions of the Hazardous Substances Act.

The information given in these data is based on the testing methods established by Leuna-Harze GmbH and on the knowledge of the characteristics of Epilox[®]- products and is given in good faith. No liability is accepted by Leuna-Harze GmbH for any system or application in which Epilox[®]- products are utilized.